


2024.4

GraphiteTIM (Low thermal resistance PGS)






Feature

- Achievable low thermal resistance equivalent to grease.
- High reliability compared to grease due to its property of barely changing thermal resistance.
- Easy handling (inventory control, repair, and processing)

Application notes

Industry	Requirements				
Power module (IGBT)	 Reliability that can withstand continuous use at 200 °C or higher. Handling, repair work, maintenance improvement. Requirement for materials that can be processed into shapes. 				
Server base station	Materials having high reliability that can reduce maintenance after installment.				

Usage example



Characteristic (Reference)

Items	Test method	Condition	Data		
Thickness (µm)	-	•	200	250	350
Thermal resistance (K·cm²/W)*1	TIM tester	200 kPa	0.6	0.4	0.5
Compressibility (%)*1	TIM tester	600 kPa	40	55	55
Flame resistance	UL-94	-	V-0 Equivalent		
Operating temperature range (℃)	-		-55 to +400		

*1: Measuring device TIM Tester (ANALYSIS TECH, ASTMD5470 compliant)


Isuue: Panasonic Industry Co., Ltd. Device Solutions Business Division

[※] A conductive material. Please use it for the parts that do not require insulation.


[※] The data shown are typical values, not guaranteed values.

Features of GraphiteTIM

1. Low thermal resistance Thermal resistance compared to grease with different thermal conductivity (Thickness of grease is 100 µm) 1.8 EYGS (t:200 μm) EYGR (t:250 µm) EYGR (t:350 µm) EYGS_100 µm (PGS) Γhermal resistance (K ⋅ cm²/W) Thermal Grease (1W/m · K)* Thermal Grease (2W/m · K)* Thermal Grease (3W/m · K)* 0.8 0.6 0.4 Pressure (kPa) Measuring device: TIM Tester (ANALYSIS TECH, ASTMD5470 compliant) Achievable low thermal resistance equivalent to grease







GraphiteTIM



Power module compatible GraphiteTIM Search Tool



Solving Thermal Grease Issues by Using Graphite TIM



https://industrial.panasonic.com/ww/soft-pgs-cross

https://industrial.panasonic.com/ww/ss/technical/p4