

**Data Sheet**

**Low transmission loss Highly heat resistant  
Multi-layer circuit board materials**

Halogen-free

**MEGTRON<sup>2</sup>**

Laminate R-1577  
Prepreg R-1570

Aug. 2022 No.22081034

# Specification / Laminate R-1577

Property		Units	Test Method	Condition	Typical Value
THERMAL	Glass Transition Temp ( Tg )	C	DSC	As received	170
			TMA	As received	165
			DMA	As received	190
	Thermal Decomposition Temp ( Td )	C	TGA	As received	380
	Time to Delam ( T288 )	Without Cu	min	IPC TM-650 2.4.24.1	As received > 120
		With Cu	min	IPC TM-650 2.4.24.1	As received 25
	CTE : $\alpha_1$	X - axis	ppm / C	IPC TM-650 2.4.24	< Tg 14 - 16
		Y - axis	ppm / C	IPC TM-650 2.4.24	< Tg 14 - 16
		Z - axis	ppm / C	IPC TM-650 2.4.24	< Tg 34
	CTE : $\alpha_2$	Z - axis	ppm / C	IPC TM-650 2.4.24	> Tg 200
ELECTRICAL	Volume Resistivity		MΩ - cm	IPC TM-650 2.5.17.1	C-96/35/90 $1 \times 10^9$
	Surface Resistivity		MΩ	IPC TM-650 2.5.17.1	C-96/35/90 $1 \times 10^8$
	Dielectric Constant ( Dk )	@ 1MHz	-	IPC TM-650 2.5.5.9	C-24/23/50 4.30
		@ 1GHz	-	IPC TM-650 2.5.5.9	C-24/23/50 4.14
	Dissipation Factor ( Df )	@ 1MHz	-	IPC TM-650 2.5.5.9	C-24/23/50 0.009
		@ 1GHz	-	IPC TM-650 2.5.5.9	C-24/23/50 0.010
PHYSICAL	Water Absorption		%	IPC TM-650 2.6.2.1	D-24/23 0.14
	Peel Strength	1oz	kN / m	IPC TM-650 2.4.8	As Received 1.3
	Flammability		-	UL	C-48/23/50 94V-0

Sample thickness ; 32 mil ( 0.8 mm )

\* The data in the above table are not guaranteed values.

# Specification / Laminate R-1577

1MHz - 1GHz ; IPC TM650-2.5.5.9

Nominal Thickness		Cloth Style	Typical Resin Content	Typical Dk			Typical Df		
mil	mm			1MHz	100MHz	1GHz	1MHz	100MHz	1GHz
2.0	0.05	106 x 1	72%	3.97	3.83	3.80	0.011	0.011	0.011
2.5	0.06	1080 x 1	59%	4.26	4.13	4.10	0.009	0.010	0.010
3.0	0.08	1080 x 1	64%	4.14	4.01	3.98	0.010	0.010	0.011
3.5	0.09	3313 x 1	53%	4.41	4.29	4.26	0.009	0.009	0.010
4.0	0.10	3313 x 1	57%	4.30	4.18	4.14	0.009	0.010	0.010
	0.10	106 x 2	72%	3.97	3.83	3.80	0.011	0.011	0.011
4.1	0.10	2116 x 1	46%	4.60	4.50	4.47	0.008	0.009	0.009
4.5	0.11	2116 x 1	52%	4.43	4.32	4.29	0.009	0.009	0.010
5.0	0.13	2116 x 1	56%	4.33	4.21	4.18	0.009	0.010	0.010
	0.13	1080 x 2	59%	4.26	4.13	4.10	0.009	0.010	0.010
5.1	0.13	1504 x 1	42%	4.72	4.62	4.59	0.008	0.008	0.009
6.0	0.15	1080 x 2	64%	4.14	4.01	3.98	0.010	0.010	0.011
		1078 x 2	64%	4.14	4.01	3.98	0.010	0.010	0.011
6.1	0.15	1501 x 1	45%	4.63	4.53	4.50	0.008	0.009	0.009
8.0	0.20	7628 x 1	47%	4.57	4.46	4.43	0.008	0.009	0.009
	0.20	3313 x 2	56%	4.33	4.21	4.18	0.009	0.010	0.010
8.1	0.20	2116 x 2	46%	4.60	4.50	4.47	0.008	0.009	0.009
10.0	0.25	2116 x 2	57%	4.30	4.18	4.14	0.009	0.010	0.010
12.0	0.30	1501 x 2	45%	4.63	4.53	4.50	0.008	0.009	0.009
16.0	0.40	7628 x 2	47%	4.57	4.46	4.43	0.008	0.009	0.009
20.0	0.50	7628 x 2 + 2116 x 1	47%	4.57	4.46	4.43	0.008	0.009	0.009

\* The data in the above table are not guaranteed values.

# Specification / Laminate R-1577

2GHz-10GHz ; IPC TM650-2.5.5.5

Nominal Thickness		Cloth Style	Typical Resin Content	Typical Dk					Typical Df				
				2GHz	4GHz	6GHz	8GHz	10GHz	2GHz	4GHz	6GHz	8GHz	10GHz
mil	mm												
2.0	0.05	106 x 1	72%	3.78	3.77	3.76	3.74	3.72	0.012	0.013	0.014	0.014	0.015
2.5	0.06	1080 x 1	59%	4.08	4.07	4.06	4.04	4.02	0.011	0.012	0.012	0.013	0.013
3.0	0.08	1080 x 1	64%	3.95	3.95	3.94	3.92	3.90	0.011	0.012	0.013	0.013	0.014
3.5	0.09	3313 x 1	53%	4.23	4.23	4.22	4.20	4.18	0.010	0.011	0.012	0.012	0.013
4.0	0.10	3313 x 1	57%	4.13	4.12	4.11	4.09	4.08	0.010	0.012	0.012	0.013	0.013
	0.10	106 x 2	72%	3.78	3.77	3.76	3.74	3.72	0.012	0.013	0.014	0.014	0.015
4.1	0.10	2116 x 1	46%	4.44	4.43	4.42	4.41	4.39	0.009	0.010	0.011	0.011	0.012
4.5	0.11	2116 x 1	52%	4.26	4.25	4.25	4.23	4.21	0.010	0.011	0.012	0.012	0.013
5.0	0.13	2116 x 1	56%	4.15	4.14	4.14	4.12	4.10	0.010	0.011	0.012	0.013	0.013
	0.13	1080 x 2	59%	4.08	4.07	4.06	4.04	4.02	0.011	0.012	0.012	0.013	0.013
5.1	0.13	1504 x 1	42%	4.57	4.56	4.55	4.54	4.52	0.009	0.010	0.011	0.011	0.012
6.0	0.15	1080 x 2	64%	3.95	3.95	3.94	3.92	3.90	0.011	0.012	0.013	0.013	0.014
		1078 x 2	64%	3.95	3.95	3.94	3.92	3.90	0.011	0.012	0.013	0.013	0.014
6.1	0.15	1501 x 1	45%	4.47	4.46	4.45	4.44	4.42	0.009	0.010	0.011	0.012	0.012
8.0	0.20	7628 x 1	47%	4.41	4.40	4.39	4.38	4.36	0.010	0.011	0.011	0.012	0.012
	0.20	3313 x 2	56%	4.15	4.14	4.14	4.12	4.10	0.010	0.011	0.012	0.013	0.013
8.1	0.20	2116 x 2	46%	4.44	4.43	4.42	4.41	4.39	0.009	0.010	0.011	0.011	0.012
10.0	0.25	2116 x 2	57%	4.13	4.12	4.11	4.09	4.08	0.010	0.012	0.012	0.013	0.013
12.0	0.30	1501 x 2	45%	4.47	4.46	4.45	4.44	4.42	0.009	0.010	0.011	0.012	0.012
16.0	0.40	7628 x 2	47%	4.41	4.40	4.39	4.38	4.36	0.010	0.011	0.011	0.012	0.012
20.0	0.50	7628 x 2 + 2116 x 1	47%	4.41	4.40	4.39	4.38	4.36	0.010	0.011	0.011	0.012	0.012

\* The data in the above table are not guaranteed values.

# Specification / Prepreg R-1570

1MHz - 1GHz ; IPC TM650-2.5.5.9

Cloth Style	Typical Resin Content	Typical Thickness (um)	Typical Dk			Typical Df		
			1MHz	100MHz	1GHz	1MHz	100MHz	1GHz
1037	77%	59	3.85	3.70	3.67	0.011	0.012	0.012
106	68%	43	4.05	3.92	3.89	0.010	0.011	0.011
	72%	50	3.97	3.83	3.80	0.011	0.011	0.011
	76%	59	3.89	3.75	3.72	0.011	0.012	0.012
1067	67%	52	4.07	3.94	3.91	0.010	0.011	0.011
	71%	61	3.99	3.85	3.82	0.011	0.011	0.011
1080	65%	74	4.12	3.98	3.95	0.010	0.011	0.011
	69%	86	4.03	3.89	3.86	0.010	0.011	0.011
	73%	100	3.95	3.81	3.78	0.011	0.011	0.012
1078	64%	74	4.14	4.01	3.98	0.010	0.010	0.011
	68%	84	4.05	3.92	3.89	0.010	0.011	0.011
3313	58%	105	4.28	4.16	4.13	0.009	0.010	0.010
	64%	125	4.14	4.01	3.98	0.010	0.010	0.011
2116	55%	123	4.35	4.23	4.20	0.009	0.010	0.010
	58%	133	4.28	4.16	4.13	0.009	0.010	0.010
1504	51%	158	4.46	4.35	4.32	0.009	0.009	0.009
1501	51%	176	4.46	4.35	4.32	0.009	0.009	0.009
7628	48%	207	4.54	4.43	4.40	0.008	0.009	0.009
	51%	223	4.46	4.35	4.32	0.009	0.009	0.009
	54%	241	4.38	4.26	4.23	0.009	0.009	0.010

\* The data in the above table are not guaranteed values.

# Specification / Prepreg R-1570

2GHz-10GHz ; IPC TM650-2.5.5.5

Cloth Style	Typical Resin Content	Typical Thickness (um)	Typical Dk					Typical Df				
			2GHz	4GHz	6GHz	8GHz	10GHz	2GHz	4GHz	6GHz	8GHz	10GHz
1037	77%	59	3.65	3.64	3.63	3.61	3.58	0.012	0.013	0.014	0.015	0.015
106	68%	43	3.86	3.85	3.85	3.83	3.81	0.011	0.013	0.013	0.014	0.014
	72%	50	3.78	3.77	3.76	3.74	3.72	0.012	0.013	0.014	0.014	0.015
	76%	59	3.70	3.69	3.68	3.66	3.60	0.012	0.013	0.014	0.015	0.015
1067	67%	52	3.89	3.88	3.87	3.85	3.83	0.011	0.012	0.013	0.014	0.014
	71%	61	3.80	3.79	3.78	3.77	3.74	0.011	0.013	0.014	0.014	0.015
1080	65%	74	3.93	3.92	3.91	3.90	3.88	0.011	0.012	0.013	0.014	0.014
	69%	86	3.84	3.83	3.82	3.80	3.79	0.011	0.013	0.013	0.014	0.014
	73%	100	3.76	3.75	3.74	3.72	3.70	0.012	0.013	0.014	0.014	0.015
1078	64%	74	3.95	3.95	3.94	3.92	3.90	0.011	0.012	0.013	0.013	0.014
	68%	84	3.86	3.85	3.85	3.83	3.81	0.011	0.013	0.013	0.014	0.014
3313	58%	105	4.10	4.09	4.08	4.07	4.05	0.010	0.012	0.012	0.013	0.013
	64%	125	3.95	3.95	3.94	3.92	3.90	0.011	0.012	0.013	0.013	0.014
2116	55%	123	4.18	4.17	4.16	4.15	4.13	0.010	0.011	0.012	0.013	0.013
	58%	133	4.10	4.09	4.08	4.07	4.05	0.010	0.012	0.012	0.013	0.013
1504	51%	158	4.29	4.28	4.27	4.26	4.24	0.010	0.011	0.012	0.012	0.012
1501	51%	176	4.29	4.28	4.27	4.26	4.24	0.010	0.011	0.012	0.012	0.012
7628	48%	207	4.38	4.37	4.36	4.35	4.33	0.010	0.011	0.011	0.012	0.012
	51%	223	4.29	4.28	4.27	4.26	4.24	0.010	0.011	0.012	0.012	0.012
	54%	241	4.21	4.20	4.19	4.17	4.16	0.010	0.011	0.012	0.012	0.013

\* The data in the above table are not guaranteed values.

# ++ Before purchase ++

## 【Notes before you use】

- ・Please verify the suitability and fitness for intended application by quality testing, evaluation or other means at your own option before any adoption, use or change of use conditions of a product listed in the datasheet.
- ・We would like to have a delivery specifications mutually agreed for the product that you have decided to use. The agreements defined in the delivery specifications are assigned higher priority.
- ・Please note that images shown may somewhat differ from the actual product in color.
- ・Please note that specifications and external design are subject to change for product improvement without notice.
- ・For details on products in the datasheet, please contact your distributor or our sales department.

## 【Safety Information】

- ・Before using the product, please read the delivery specifications carefully or contact the distributor from which you purchased the product or our sales department in order to use the product correctly.
- ・The products in the datasheet are Electronic circuit board materials for electronic and electrical devices. Please do not use them for other than specified use.

## Please Contact us of more

### 【Technical Marketing】

- ・Japan (Osaka) TEL: 81-6-6904-2771
- ・USA (Mountain view) TEL: 1-408-861-3946
- ・Austria (Enns) TEL: 43-7223-883
- ・China (Guangzhou) TEL: 86-20-8713-0888

### 【Sales Offices】

- |                      |                       |
|----------------------|-----------------------|
| ・China (Hong Kong)   | TEL: 852-2529-3956    |
| ・China (Suzhou)      | TEL: 86-512-6825-1565 |
| ・China (Guangzhou)   | TEL: 86-20-8713-0888  |
| ・Korea (Seoul)       | TEL: 82-2-361-7873    |
| ・Taiwan (Hsinchu)    | TEL: 886-3-598-3201   |
| ・Thailand (Ayuthaya) | TEL: 66-3533-0846     |
| ・Austria (Enns)      | TEL: 43-7223-883      |
| ・USA (Mountain view) | TEL: 1-408-861-3946   |
| ・Japan (Osaka)       | TEL: 81-6-6904-2771   |

Panasonic Industry Co., Ltd.

Electronic Materials Business Division

Circuit Board Materials Business Unit.

Head Office: 1006 Kadoma, Kadoma City, Osaka 571-8506

TEL: 81-6-6908-1101

[industrial.panasonic.com/ww/electronic-materials](http://industrial.panasonic.com/ww/electronic-materials)