

Data Sheet

High Speed, Low Loss Multi-layer Materials

MEGTRON7(G)

| | | Guangzhou | Koriyama |
|---|----------|------------|-------------|
| E glass type | Laminate | R-5785(GE) | R-5785(1)* |
| | Prepreg | R-5680(GE) | R-5680(1)* |
| <small>*On the label, described as "GE type"</small> | | | |
| Low-Dk glass type | Laminate | R-5785(GN) | R-5785(2)** |
| | Prepreg | R-5680(GN) | R-5680(2)** |
| <small>**On the label, described as "GN type"</small> | | | |

Apr. 2022 No.22040128

Specification / Laminate R-5785(GE) & R-5785(GN)

| Property | | Units | Test Method | Condition | Typical Value | | | |
|------------------|-----------------------------------|----------------|-----------------|---------------------|-----------------------|----------------------------|---------------------|---------------|
| | | | | | R-5785(GE) E glass | R-5785(GN) Low-Dk glass | | |
| THERMAL | Glass Transition Temp (Tg) | | C | DSC | As received | 200 | 200 | |
| | | | | TMA | As received | 190 | 190 | |
| | | | | DMA | As received | 210 | 210 | |
| | Thermal Decomposition Temp (Td) | | C | TGA | As received | 400 | 400 | |
| | Time to Delam (T288) | | Without Cu | Min | IPC TM-650 2.4.24.1 | As received | > 120 | > 120 |
| | | | With Cu | Min | IPC TM-650 2.4.24.1 | As received | > 120 | > 120 |
| | CTE : $\alpha 1$ | | X – axis | ppm / C | IPC TM-650 2.4.24 | < Tg | 14 - 16 | 14 - 16 |
| | | | Y – axis | ppm / C | IPC TM-650 2.4.24 | < Tg | 14 - 16 | 14 - 16 |
| Z – axis | | | ppm / C | IPC TM-650 2.4.24 | < Tg | 42 | 42 | |
| CTE : $\alpha 2$ | | Z – axis | ppm / C | IPC TM-650 2.4.24 | > Tg | 280 | 280 | |
| ELECTRICAL | Volume Resistivity | | M Ω - cm | IPC TM-650 2.5.17.1 | C-96/35/90 | 1 x 10 ⁹ | 1 x 10 ⁹ | |
| | Surface Resistivity | | M Ω | IPC TM-650 2.5.17.1 | C-96/35/90 | 1 x 10 ⁸ | 1 x 10 ⁸ | |
| | Dielectric Constant (Dk) | | @ 1GHz | - | IPC TM-650 2.5.5.9 | C-24/23/50 | 3.63 | 3.37 |
| | | | @ 13, 14GHz | - | *Note 1 | C-24/23/50 | 3.60 @13GHz | 3.31 @14GHz |
| | Dissipation Factor (Df) | | @ 1GHz | - | IPC TM-650 2.5.5.9 | C-24/23/50 | 0.002 | 0.001 |
| | | | @ 13, 14GHz | - | *Note 1 | C-24/23/50 | 0.0034 @13GHz | 0.0023 @14GHz |
| PHYSICAL | Water Absorption | | % | IPC TM-650 2.6.2.1 | D-24/23 | 0.06 | 0.06 | |
| | Peel Strength | 1oz (H-VLP2) | kN / m | IPC TM-650 2.4.8 | As received | 0.8 | 0.8 | |
| | Flammability | | - | UL | C-48/23/50 | 94V-0 | 94V-0 | |

Sample thickness : 29.5 mil = 0.750 mm (Core Type 30)

Note 1 : Balanced-type Circular Disk Resonance Method [IEC 63185 (2020)]

* The data in the above table are not guaranteed values.

Specification / Laminate R-5785(GE) : E glass

1GHz ; IPC TM650-2.5.5.9

13-58GHz ; Balanced-type Circular Disk Resonance Method [IEC 63185 (2020)]

| Core Type | Actual Thickness | | Cloth Style | ply | Typical Resin Content (%) | Core Labeling | Typical Dk | | | | | |
|-----------|------------------|-------|-------------|-----|---------------------------|---------------|------------|-------|-------|-------|-------|-------|
| | mil | mm | | | | | 1GHz | 13GHz | 24GHz | 36GHz | 47GHz | 58GHz |
| 2 | 2.0 | 0.050 | 1035 | 1 | 65 | 0.05 | 3.37 | 3.34 | 3.34 | 3.34 | 3.34 | 3.34 |
| 2.6 | 2.6 | 0.065 | 1078 | 1 | 57 | 0.07 | 3.55 | 3.51 | 3.51 | 3.51 | 3.51 | 3.51 |
| 3 | 3.0 | 0.075 | 1078 | 1 | 63 | 0.08 | 3.41 | 3.38 | 3.38 | 3.38 | 3.38 | 3.38 |
| 3.5 | 3.5 | 0.090 | 1078 | 1 | 68 | 0.09 | 3.30 | 3.29 | 3.29 | 3.29 | 3.29 | 3.29 |
| 4 | 3.9 | 0.100 | 3313 | 1 | 53 | 0.1 | 3.63 | 3.60 | 3.60 | 3.60 | 3.60 | 3.60 |
| 4 | 3.9 | 0.100 | 1035 | 2 | 65 | 0.1 | 3.37 | 3.34 | 3.34 | 3.34 | 3.34 | 3.34 |
| 5 | 5.0 | 0.127 | 1078 | 2 | 57 | 0.12 | 3.55 | 3.51 | 3.51 | 3.51 | 3.51 | 3.51 |
| 5 | 4.9 | 0.125 | 2116 | 1 | 53 | 0.13 | 3.63 | 3.60 | 3.60 | 3.60 | 3.60 | 3.60 |
| 6 | 5.7 | 0.146 | 1078 | 2 | 63 | 0.14 | 3.41 | 3.38 | 3.38 | 3.38 | 3.38 | 3.38 |
| 7 | 7.0 | 0.178 | 1078 | 2 | 68 | 0.18 | 3.30 | 3.29 | 3.29 | 3.29 | 3.29 | 3.29 |
| 8 | 7.9 | 0.200 | 3313 | 2 | 53 | 0.2 | 3.63 | 3.60 | 3.60 | 3.60 | 3.60 | 3.60 |
| 10 | 9.8 | 0.250 | 2116 | 2 | 53 | 0.25 | 3.63 | 3.60 | 3.60 | 3.60 | 3.60 | 3.60 |
| 12 | 11.8 | 0.300 | 3313 | 3 | 53 | 0.3 | 3.63 | 3.60 | 3.60 | 3.60 | 3.60 | 3.60 |
| 16 | 15.7 | 0.400 | 3313 | 4 | 53 | 0.4 | 3.63 | 3.60 | 3.60 | 3.60 | 3.60 | 3.60 |
| 20 | 19.7 | 0.500 | 2116 | 4 | 53 | 0.5 | 3.63 | 3.60 | 3.60 | 3.60 | 3.60 | 3.60 |
| 25 | 24.6 | 0.625 | 2116 | 5 | 53 | 0.63 | 3.63 | 3.60 | 3.60 | 3.60 | 3.60 | 3.60 |
| 30 | 29.5 | 0.750 | 2116 | 6 | 53 | 0.75 | 3.63 | 3.60 | 3.60 | 3.60 | 3.60 | 3.60 |

* The data in the above table are not guaranteed values.

Specification / Laminate R-5785(GE) : E glass

1GHz ; IPC TM650-2.5.5.9

13-58GHz ; Balanced-type Circular Disk Resonance Method [IEC 63185 (2020)]

| Core Type | Actual Thickness | | Cloth Style | ply | Typical Resin Content (%) | Core Labeling | Typical Df | | | | | |
|-----------|------------------|-------|-------------|-----|---------------------------|---------------|------------|--------|--------|--------|--------|--------|
| | mil | mm | | | | | 1GHz | 13GHz | 24GHz | 36GHz | 47GHz | 58GHz |
| 2 | 2.0 | 0.050 | 1035 | 1 | 65 | 0.05 | 0.002 | 0.0029 | 0.0032 | 0.0035 | 0.0038 | 0.0041 |
| 2.6 | 2.6 | 0.065 | 1078 | 1 | 57 | 0.07 | 0.002 | 0.0032 | 0.0035 | 0.0039 | 0.0043 | 0.0046 |
| 3 | 3.0 | 0.075 | 1078 | 1 | 63 | 0.08 | 0.002 | 0.0029 | 0.0033 | 0.0036 | 0.0039 | 0.0043 |
| 3.5 | 3.5 | 0.090 | 1078 | 1 | 68 | 0.09 | 0.002 | 0.0028 | 0.0031 | 0.0034 | 0.0037 | 0.0040 |
| 4 | 3.9 | 0.100 | 3313 | 1 | 53 | 0.1 | 0.002 | 0.0034 | 0.0037 | 0.0041 | 0.0045 | 0.0049 |
| 4 | 3.9 | 0.100 | 1035 | 2 | 65 | 0.1 | 0.002 | 0.0029 | 0.0032 | 0.0035 | 0.0038 | 0.0041 |
| 5 | 5.0 | 0.127 | 1078 | 2 | 57 | 0.12 | 0.002 | 0.0032 | 0.0035 | 0.0039 | 0.0043 | 0.0046 |
| 5 | 4.9 | 0.125 | 2116 | 1 | 53 | 0.13 | 0.002 | 0.0034 | 0.0037 | 0.0041 | 0.0045 | 0.0049 |
| 6 | 5.7 | 0.146 | 1078 | 2 | 63 | 0.14 | 0.002 | 0.0029 | 0.0033 | 0.0036 | 0.0039 | 0.0043 |
| 7 | 7.0 | 0.178 | 1078 | 2 | 68 | 0.18 | 0.002 | 0.0028 | 0.0031 | 0.0034 | 0.0037 | 0.0040 |
| 8 | 7.9 | 0.200 | 3313 | 2 | 53 | 0.2 | 0.002 | 0.0034 | 0.0037 | 0.0041 | 0.0045 | 0.0049 |
| 10 | 9.8 | 0.250 | 2116 | 2 | 53 | 0.25 | 0.002 | 0.0034 | 0.0037 | 0.0041 | 0.0045 | 0.0049 |
| 12 | 11.8 | 0.300 | 3313 | 3 | 53 | 0.3 | 0.002 | 0.0034 | 0.0037 | 0.0041 | 0.0045 | 0.0049 |
| 16 | 15.7 | 0.400 | 3313 | 4 | 53 | 0.4 | 0.002 | 0.0034 | 0.0037 | 0.0041 | 0.0045 | 0.0049 |
| 20 | 19.7 | 0.500 | 2116 | 4 | 53 | 0.5 | 0.002 | 0.0034 | 0.0037 | 0.0041 | 0.0045 | 0.0049 |
| 25 | 24.6 | 0.625 | 2116 | 5 | 53 | 0.63 | 0.002 | 0.0034 | 0.0037 | 0.0041 | 0.0045 | 0.0049 |
| 30 | 29.5 | 0.750 | 2116 | 6 | 53 | 0.75 | 0.002 | 0.0034 | 0.0037 | 0.0041 | 0.0045 | 0.0049 |

* The data in the above table are not guaranteed values.

Specification / Prepreg R-5680(GE) : E glass

1GHz ; IPC TM650-2.5.5.9

13-58GHz ; Balanced-type Circular Disk Resonance Method [IEC 63185 (2020)]

| Cloth Style | Resin Content (%) | Typical Thickness (um) | Prepreg labeling | Typical Dk | | | | | |
|-------------|-------------------|------------------------|------------------|------------|-------|-------|-------|-------|-------|
| | | | | 1GHz | 13GHz | 24GHz | 36GHz | 47GHz | 58GHz |
| 1035 | 70 | 60 | 0.04 | 3.26 | 3.25 | 3.25 | 3.25 | 3.25 | 3.25 |
| | 73 | 68 | | 3.20 | 3.20 | 3.20 | 3.20 | 3.20 | 3.20 |
| | 75 | 74 | | 3.18 | 3.16 | 3.16 | 3.16 | 3.16 | 3.16 |
| 1080 | 64 | 76 | 0.06 | 3.39 | 3.36 | 3.36 | 3.36 | 3.36 | 3.36 |
| | 68 | 87 | | 3.30 | 3.29 | 3.29 | 3.29 | 3.29 | 3.29 |
| | 72 | 101 | | 3.22 | 3.21 | 3.21 | 3.21 | 3.21 | 3.21 |
| | 75 | 115 | | 3.18 | 3.16 | 3.16 | 3.16 | 3.16 | 3.16 |
| 1078 | 64 | 77 | 0.06 | 3.39 | 3.36 | 3.36 | 3.36 | 3.36 | 3.36 |
| | 68 | 89 | | 3.30 | 3.29 | 3.29 | 3.29 | 3.29 | 3.29 |
| | 72 | 104 | | 3.22 | 3.21 | 3.21 | 3.21 | 3.21 | 3.21 |
| | 75 | 118 | | 3.18 | 3.16 | 3.16 | 3.16 | 3.16 | 3.16 |
| 3313 | 54 | 98 | 0.08 | 3.63 | 3.58 | 3.58 | 3.58 | 3.58 | 3.58 |
| | 57 | 106 | | 3.55 | 3.51 | 3.51 | 3.51 | 3.51 | 3.51 |
| 2116 | 56 | 132 | 0.1 | 3.57 | 3.53 | 3.53 | 3.53 | 3.53 | 3.53 |

* The data in the above table are not guaranteed values.

Specification / Prepreg R-5680(GE) : E glass

1GHz ; IPC TM650-2.5.5.9

13-58GHz ; Balanced-type Circular Disk Resonance Method [IEC 63185 (2020)]

| Cloth Style | Resin Content (%) | Typical Thickness (um) | Prepreg labeling | Typical Df | | | | | |
|-------------|-------------------|------------------------|------------------|------------|--------|--------|--------|--------|--------|
| | | | | 1GHz | 13GHz | 24GHz | 36GHz | 47GHz | 58GHz |
| 1035 | 70 | 60 | 0.04 | 0.002 | 0.0027 | 0.0030 | 0.0033 | 0.0036 | 0.0039 |
| | 73 | 68 | | 0.002 | 0.0026 | 0.0028 | 0.0031 | 0.0034 | 0.0037 |
| | 75 | 74 | | 0.002 | 0.0025 | 0.0028 | 0.0031 | 0.0033 | 0.0036 |
| 1080 | 64 | 76 | 0.06 | 0.002 | 0.0029 | 0.0032 | 0.0036 | 0.0039 | 0.0042 |
| | 68 | 87 | | 0.002 | 0.0028 | 0.0031 | 0.0034 | 0.0037 | 0.0040 |
| | 72 | 101 | | 0.002 | 0.0026 | 0.0029 | 0.0032 | 0.0035 | 0.0038 |
| | 75 | 115 | | 0.002 | 0.0025 | 0.0028 | 0.0031 | 0.0033 | 0.0036 |
| 1078 | 64 | 77 | 0.06 | 0.002 | 0.0029 | 0.0032 | 0.0036 | 0.0039 | 0.0042 |
| | 68 | 89 | | 0.002 | 0.0028 | 0.0031 | 0.0034 | 0.0037 | 0.0040 |
| | 72 | 104 | | 0.002 | 0.0026 | 0.0029 | 0.0032 | 0.0035 | 0.0038 |
| | 75 | 118 | | 0.002 | 0.0025 | 0.0028 | 0.0031 | 0.0033 | 0.0036 |
| 3313 | 54 | 98 | 0.08 | 0.002 | 0.0033 | 0.0037 | 0.0041 | 0.0044 | 0.0048 |
| | 57 | 106 | | 0.002 | 0.0032 | 0.0035 | 0.0039 | 0.0043 | 0.0046 |
| 2116 | 56 | 132 | 0.1 | 0.002 | 0.0032 | 0.0036 | 0.0040 | 0.0043 | 0.0047 |

* The data in the above table are not guaranteed values.

Specification / Laminate R-5785(GN) : Low-Dk glass

1GHz ; IPC TM650-2.5.5.9

14-59GHz ; Balanced-type Circular Disk Resonance Method [IEC 63185 (2020)]

| Core Type | Actual Thickness | | Cloth Style | ply | Typical Resin Content (%) | Core Labeling | Typical Dk | | | | | |
|-----------|------------------|-------|-------------|-----|---------------------------|---------------|------------|-------|-------|-------|-------|-------|
| | mil | mm | | | | | 1GHz | 14GHz | 25GHz | 36GHz | 48GHz | 59GHz |
| 2 | 2.0 | 0.050 | 1035 | 1 | 67 | 0.05 | 3.21 | 3.15 | 3.15 | 3.15 | 3.15 | 3.15 |
| 2.6 | 2.6 | 0.065 | 1078 | 1 | 59 | 0.07 | 3.32 | 3.25 | 3.25 | 3.25 | 3.25 | 3.25 |
| 3 | 3.0 | 0.075 | 1078 | 1 | 65 | 0.08 | 3.24 | 3.17 | 3.17 | 3.17 | 3.17 | 3.17 |
| 3.5 | 3.5 | 0.090 | 1078 | 1 | 70 | 0.09 | 3.18 | 3.11 | 3.11 | 3.11 | 3.11 | 3.11 |
| 4 | 3.9 | 0.100 | 2013 | 1 | 55 | 0.1 | 3.37 | 3.31 | 3.31 | 3.31 | 3.31 | 3.31 |
| 4 | 3.9 | 0.100 | 1035 | 2 | 67 | 0.1 | 3.21 | 3.15 | 3.15 | 3.15 | 3.15 | 3.15 |
| 5 | 5.0 | 0.127 | 1078 | 2 | 59 | 0.12 | 3.32 | 3.25 | 3.25 | 3.25 | 3.25 | 3.25 |
| 5 | 4.9 | 0.125 | 2116 | 1 | 55 | 0.13 | 3.37 | 3.31 | 3.31 | 3.31 | 3.31 | 3.31 |
| 6 | 5.7 | 0.146 | 1078 | 2 | 65 | 0.14 | 3.24 | 3.17 | 3.17 | 3.17 | 3.17 | 3.17 |
| 7 | 7.0 | 0.178 | 1078 | 2 | 70 | 0.18 | 3.18 | 3.11 | 3.11 | 3.11 | 3.11 | 3.11 |
| 8 | 7.9 | 0.200 | 2013 | 2 | 55 | 0.2 | 3.37 | 3.31 | 3.31 | 3.31 | 3.31 | 3.31 |
| 10 | 9.8 | 0.250 | 2116 | 2 | 55 | 0.25 | 3.37 | 3.31 | 3.31 | 3.31 | 3.31 | 3.31 |
| 12 | 11.8 | 0.300 | 2013 | 3 | 55 | 0.3 | 3.37 | 3.31 | 3.31 | 3.31 | 3.31 | 3.31 |
| 16 | 15.7 | 0.400 | 2013 | 4 | 55 | 0.4 | 3.37 | 3.31 | 3.31 | 3.31 | 3.31 | 3.31 |
| 20 | 19.7 | 0.500 | 2116 | 4 | 55 | 0.5 | 3.37 | 3.31 | 3.31 | 3.31 | 3.31 | 3.31 |
| 25 | 24.6 | 0.625 | 2116 | 5 | 55 | 0.63 | 3.37 | 3.31 | 3.31 | 3.31 | 3.31 | 3.31 |
| 30 | 29.5 | 0.750 | 2116 | 6 | 55 | 0.75 | 3.37 | 3.31 | 3.31 | 3.31 | 3.31 | 3.31 |

* The data in the above table are not guaranteed values.

Specification / Laminate R-5785(GN) : Low-Dk glass

1GHz ; IPC TM650-2.5.5.9

14-59GHz ; Balanced-type Circular Disk Resonance Method [IEC 63185 (2020)]

| Core Type | Actual Thickness | | Cloth Style | ply | Typical Resin Content (%) | Core Labeling | Typical Df | | | | | |
|-----------|------------------|-------|-------------|-----|-----------------------------|---------------|------------|--------|--------|--------|--------|--------|
| | mil | mm | | | | | 1GHz | 14GHz | 25GHz | 36GHz | 48GHz | 59GHz |
| 2 | 2.0 | 0.050 | 1035 | 1 | 67 | 0.05 | 0.001 | 0.0021 | 0.0023 | 0.0026 | 0.0028 | 0.0030 |
| 2.6 | 2.6 | 0.065 | 1078 | 1 | 59 | 0.07 | 0.001 | 0.0022 | 0.0025 | 0.0027 | 0.0030 | 0.0032 |
| 3 | 3.0 | 0.075 | 1078 | 1 | 65 | 0.08 | 0.001 | 0.0021 | 0.0024 | 0.0026 | 0.0028 | 0.0031 |
| 3.5 | 3.5 | 0.090 | 1078 | 1 | 70 | 0.09 | 0.001 | 0.0021 | 0.0023 | 0.0025 | 0.0028 | 0.0030 |
| 4 | 3.9 | 0.100 | 2013 | 1 | 55 | 0.1 | 0.001 | 0.0023 | 0.0025 | 0.0028 | 0.0030 | 0.0033 |
| 4 | 3.9 | 0.100 | 1035 | 2 | 67 | 0.1 | 0.001 | 0.0021 | 0.0023 | 0.0026 | 0.0028 | 0.0030 |
| 5 | 5.0 | 0.127 | 1078 | 2 | 59 | 0.12 | 0.001 | 0.0022 | 0.0025 | 0.0027 | 0.0030 | 0.0032 |
| 5 | 4.9 | 0.125 | 2116 | 1 | 55 | 0.13 | 0.001 | 0.0023 | 0.0025 | 0.0028 | 0.0030 | 0.0033 |
| 6 | 5.7 | 0.146 | 1078 | 2 | 65 | 0.14 | 0.001 | 0.0021 | 0.0024 | 0.0026 | 0.0028 | 0.0031 |
| 7 | 7.0 | 0.178 | 1078 | 2 | 70 | 0.18 | 0.001 | 0.0021 | 0.0023 | 0.0025 | 0.0028 | 0.0030 |
| 8 | 7.9 | 0.200 | 2013 | 2 | 55 | 0.2 | 0.001 | 0.0023 | 0.0025 | 0.0028 | 0.0030 | 0.0033 |
| 10 | 9.8 | 0.250 | 2116 | 2 | 55 | 0.25 | 0.001 | 0.0023 | 0.0025 | 0.0028 | 0.0030 | 0.0033 |
| 12 | 11.8 | 0.300 | 2013 | 3 | 55 | 0.3 | 0.001 | 0.0023 | 0.0025 | 0.0028 | 0.0030 | 0.0033 |
| 16 | 15.7 | 0.400 | 2013 | 4 | 55 | 0.4 | 0.001 | 0.0023 | 0.0025 | 0.0028 | 0.0030 | 0.0033 |
| 20 | 19.7 | 0.500 | 2116 | 4 | 55 | 0.5 | 0.001 | 0.0023 | 0.0025 | 0.0028 | 0.0030 | 0.0033 |
| 25 | 24.6 | 0.625 | 2116 | 5 | 55 | 0.63 | 0.001 | 0.0023 | 0.0025 | 0.0028 | 0.0030 | 0.0033 |
| 30 | 29.5 | 0.750 | 2116 | 6 | 55 | 0.75 | 0.001 | 0.0023 | 0.0025 | 0.0028 | 0.0030 | 0.0033 |

* The data in the above table are not guaranteed values.

Specification / Prepreg R-5680(GN) : Low-Dk glass

1GHz ; IPC TM650-2.5.5.9

14-59GHz ; Balanced-type Circular Disk Resonance Method [IEC 63185 (2020)]

| Cloth Style | Resin Content (%) | Typical Thickness (um) | Prepreg labeling | Typical Dk | | | | | |
|-------------|-------------------|------------------------|------------------|------------|-------|-------|-------|-------|-------|
| | | | | 1GHz | 14GHz | 25GHz | 36GHz | 48GHz | 59GHz |
| 1035 | 72 | 60 | 0.04 | 3.15 | 3.09 | 3.09 | 3.09 | 3.09 | 3.09 |
| | 75 | 68 | | 3.11 | 3.05 | 3.05 | 3.05 | 3.05 | 3.05 |
| | 77 | 74 | | 3.09 | 3.03 | 3.03 | 3.03 | 3.03 | 3.03 |
| 1080 | 66 | 77 | 0.06 | 3.23 | 3.16 | 3.16 | 3.16 | 3.16 | 3.16 |
| | 70 | 87 | | 3.18 | 3.11 | 3.11 | 3.11 | 3.11 | 3.11 |
| | 74 | 102 | | 3.12 | 3.06 | 3.06 | 3.06 | 3.06 | 3.06 |
| | 77 | 115 | | 3.09 | 3.03 | 3.03 | 3.03 | 3.03 | 3.03 |
| 1078 | 66 | 77 | 0.06 | 3.23 | 3.16 | 3.16 | 3.16 | 3.16 | 3.16 |
| | 70 | 89 | | 3.18 | 3.11 | 3.11 | 3.11 | 3.11 | 3.11 |
| | 74 | 104 | | 3.12 | 3.06 | 3.06 | 3.06 | 3.06 | 3.06 |
| | 77 | 118 | | 3.09 | 3.03 | 3.03 | 3.03 | 3.03 | 3.03 |
| 2013 | 56 | 100 | 0.08 | 3.37 | 3.30 | 3.30 | 3.30 | 3.30 | 3.30 |
| | 59 | 109 | | 3.32 | 3.25 | 3.25 | 3.25 | 3.25 | 3.25 |
| 2116 | 58 | 132 | 0.1 | 3.33 | 3.27 | 3.27 | 3.27 | 3.27 | 3.27 |

* The data in the above table are not guaranteed values.

Specification / Prepreg R-5680(GN) : Low-Dk glass

1GHz ; IPC TM650-2.5.5.9

14-59GHz ; Balanced-type Circular Disk Resonance Method [IEC 63185 (2020)]

| Cloth Style | Resin Content (%) | Typical Thickness (um) | Prepreg labeling | Typical Df | | | | | |
|-------------|-------------------|------------------------|------------------|------------|--------|--------|--------|--------|--------|
| | | | | 1GHz | 14GHz | 25GHz | 36GHz | 48GHz | 59GHz |
| 1035 | 72 | 60 | 0.04 | 0.001 | 0.0020 | 0.0023 | 0.0025 | 0.0027 | 0.0029 |
| | 75 | 68 | | 0.001 | 0.0020 | 0.0022 | 0.0024 | 0.0027 | 0.0029 |
| | 77 | 74 | | 0.001 | 0.0020 | 0.0022 | 0.0024 | 0.0026 | 0.0028 |
| 1080 | 66 | 77 | 0.06 | 0.001 | 0.0021 | 0.0024 | 0.0026 | 0.0028 | 0.0031 |
| | 70 | 87 | | 0.001 | 0.0021 | 0.0023 | 0.0025 | 0.0028 | 0.0030 |
| | 74 | 102 | | 0.001 | 0.0020 | 0.0022 | 0.0025 | 0.0027 | 0.0029 |
| | 77 | 115 | | 0.001 | 0.0020 | 0.0022 | 0.0024 | 0.0026 | 0.0028 |
| 1078 | 66 | 77 | 0.06 | 0.001 | 0.0021 | 0.0024 | 0.0026 | 0.0028 | 0.0031 |
| | 70 | 89 | | 0.001 | 0.0021 | 0.0023 | 0.0025 | 0.0028 | 0.0030 |
| | 74 | 104 | | 0.001 | 0.0020 | 0.0022 | 0.0025 | 0.0027 | 0.0029 |
| | 77 | 118 | | 0.001 | 0.0020 | 0.0022 | 0.0024 | 0.0026 | 0.0028 |
| 2013 | 56 | 100 | 0.08 | 0.001 | 0.0023 | 0.0025 | 0.0028 | 0.0030 | 0.0033 |
| | 59 | 109 | | 0.001 | 0.0022 | 0.0025 | 0.0027 | 0.0030 | 0.0032 |
| 2116 | 58 | 132 | 0.1 | 0.001 | 0.0022 | 0.0025 | 0.0027 | 0.0030 | 0.0032 |

* The data in the above table are not guaranteed values.

++ Before purchase ++

【Notes before you use】

- Please verify the suitability and fitness for intended application by quality testing, evaluation or other means at your own option before any adoption, use or change of use conditions of a product listed in the datasheet.
- We would like to have a delivery specifications mutually agreed for the product that you have decided to use. The agreements defined in the delivery specifications are assigned higher priority.
- Please note that images shown may somewhat differ from the actual product in color.
- Please note that specifications and external design are subject to change for product improvement without notice.
- For details on products in the datasheet, please contact your distributor or our sales department.

【Safety Information】

- Before using the product, please read the delivery specifications carefully or contact the distributor from which you purchased the product or our sales department in order to use the product correctly.
- The products in the datasheet are Electronic circuit board materials for electronic and electrical devices. Please do not use them for other than specified use.

Please Contact us of more

【Technical Marketing】

- Japan (Osaka) TEL: 81-6-6904-2771
- USA (Mountain view) TEL: 1-408-861-3946
- Austria (Enns) TEL: 43-7223-883
- China (Guangzhou) TEL: 86-20-8713-0888

【Sales Offices】

- China (Hong Kong) TEL: 852-2529-3956
- China (Suzhou) TEL: 86-512-6825-1565
- China (Guangzhou) TEL: 86-20-8713-0888
- Korea (Seoul) TEL: 82-2-361-7873
- Taiwan (Hsinchu) TEL: 886-3-598-3201
- Thailand (Ayuthaya) TEL: 66-3533-0846
- Austria (Enns) TEL: 43-7223-883
- USA (Mountain view) TEL: 1-408-861-3946
- Japan (Osaka) TEL: 81-6-6904-2771

Panasonic Industry Co., Ltd.
 Electronic Materials Business Division
 Circuit Board Materials Business Unit.
 Head Office: 1006 Kadoma, Kadoma City, Osaka 571-8506
 TEL: 81-6-6908-1101
industrial.panasonic.com/ww/electronic-materials