

Data Sheet

Low Dk Halogen-free

Multi-layer Materials

Halogen-free

Laminate R-A555(W)
Prepreg R-A550(W)

July 2022 No.22070144

Specification / Laminate R-A555(W)

Property		Units	Test Method	Condition	Typical Value	
THERMAL	Glass Transition Temp (Tg)	°C	TMA	As received	160	
			DMA	As received	200	
	Thermal Decomposition Temp (Td)		°C	TGA	As received	380
	Time to Delam (T288)	Without Cu	Min	IPC TM-650 2.4.24.1	As received	> 60
		With Cu	Min	IPC TM-650 2.4.24.1	As received	> 60
	CTE : $\alpha 1$	X - axis	ppm / C	IPC TM-650 2.4.24	< Tg	11 – 13
		Y - axis	ppm / C	IPC TM-650 2.4.24	< Tg	13 – 15
		Z - axis	ppm / C	IPC TM-650 2.4.24	< Tg	37
CTE : $\alpha 2$	Z – axis	ppm / C	IPC TM-650 2.4.24	> Tg	170	
ELECTRICAL	Volume Resistivity		M Ω - cm	IPC TM-650 2.5.17.1	C-96/35/90	1 x 10 ⁹
	Surface Resistivity		M Ω	IPC TM-650 2.5.17.1	C-96/35/90	1 x 10 ⁸
	Dielectric Constant (Dk) (RC : 70%)	@ 1GHz	-	IPC TM-650 2.5.5.9	C-24/23/50	3.4
		@ 10GHz	-	IPC TM-650 2.5.5.5	C-24/23/50	3.2
	Dissipation Factor (Df) (RC : 70%)	@ 1GHz	-	IPC TM-650 2.5.5.9	C-24/23/50	0.008
		@ 10GHz	-	IPC TM-650 2.5.5.5	C-24/23/50	0.011
PHYSICAL	Water Absorption		%	IPC TM-650 2.6.2.1	D-24/23	0.07
	Flammability		-	UL	C-48/23/50	94V-0

Sample thickness ; 32 mil (0.8 mm)

* The data in the above table are not guaranteed values.

Specification / Laminate R-A555(W) Dk, Df

1GHz ; IPC TM650-2.5.5.9 2GHz-10GHz ; IPC TM650-2.5.5.5

Core Type	Actual Thickness		Cloth Style	ply	Typical Resin Content	Typical Dk						Typical Df					
	mil	mm				1GHz	2GHz	4GHz	6GHz	8GHz	10GHz	1GHz	2GHz	4GHz	6GHz	8GHz	10GHz
1.6	1.6	0.040	1037	1	66	3.5	3.5	3.5	3.4	3.4	3.3	0.008	0.010	0.010	0.010	0.010	0.011
2.0	2.0	0.050	1037	1	72	3.4	3.4	3.4	3.3	3.3	3.2	0.008	0.010	0.010	0.010	0.010	0.011
2.0	2.0	0.050	106	1	68	3.4	3.4	3.4	3.3	3.3	3.2	0.008	0.010	0.010	0.010	0.010	0.011
2.0	2.0	0.052	1067	1	61	3.6	3.6	3.6	3.5	3.5	3.4	0.007	0.009	0.009	0.009	0.009	0.010
2.5	2.4	0.062	1080	1	54	3.8	3.8	3.8	3.7	3.7	3.6	0.007	0.009	0.009	0.009	0.009	0.010
2.3	2.4	0.062	1078	1	54	3.8	3.8	3.8	3.7	3.7	3.6	0.007	0.009	0.009	0.009	0.009	0.010

* The data in the above table are not guaranteed values.

Specification / Prepreg R-A550(W) Dk, Df

1GHz ; IPC TM650-2.5.5.9 2GHz-10GHz ; IPC TM650-2.5.5.5

Cloth Style	Resin Content (%)	Typical Thickness (um)	Typical Dk						Typical Df					
			1GHz	2GHz	4GHz	6GHz	8GHz	10GHz	1GHz	2GHz	4GHz	6GHz	8GHz	10GHz
1017	76	33	3.3	3.3	3.3	3.2	3.2	3.1	0.008	0.010	0.010	0.010	0.010	0.011
	78	36	3.3	3.3	3.3	3.2	3.2	3.1	0.008	0.010	0.010	0.010	0.010	0.011
1027	68	38	3.4	3.4	3.4	3.3	3.3	3.2	0.008	0.010	0.010	0.010	0.010	0.011
	70	41	3.4	3.4	3.4	3.3	3.3	3.2	0.008	0.010	0.010	0.010	0.010	0.011
	73	46	3.3	3.3	3.3	3.2	3.2	3.1	0.008	0.010	0.010	0.010	0.010	0.011
	75	51	3.3	3.3	3.3	3.2	3.2	3.1	0.008	0.010	0.010	0.010	0.010	0.011
	77	55	3.3	3.3	3.3	3.2	3.2	3.1	0.008	0.010	0.010	0.010	0.010	0.011
1037	67	42	3.5	3.5	3.5	3.4	3.4	3.3	0.008	0.010	0.010	0.010	0.010	0.011
	69	46	3.4	3.4	3.4	3.3	3.3	3.2	0.008	0.010	0.010	0.010	0.010	0.011
	72	51	3.4	3.4	3.4	3.3	3.3	3.2	0.008	0.010	0.010	0.010	0.010	0.011
	74	56	3.3	3.3	3.3	3.2	3.2	3.1	0.008	0.010	0.010	0.010	0.010	0.011
	77	64	3.3	3.3	3.3	3.2	3.2	3.1	0.008	0.010	0.010	0.010	0.010	0.011
106	72	54	3.4	3.4	3.4	3.3	3.3	3.2	0.008	0.010	0.010	0.010	0.010	0.011
	75	62	3.3	3.3	3.3	3.2	3.2	3.1	0.008	0.010	0.010	0.010	0.010	0.011
1067	67	57	3.5	3.5	3.5	3.4	3.4	3.3	0.008	0.010	0.010	0.010	0.010	0.011
	69	61	3.4	3.4	3.4	3.3	3.3	3.2	0.008	0.010	0.010	0.010	0.010	0.011
	72	69	3.4	3.4	3.4	3.3	3.3	3.2	0.008	0.010	0.010	0.010	0.010	0.011
	74	75	3.3	3.3	3.3	3.2	3.2	3.1	0.008	0.010	0.010	0.010	0.010	0.011
1078	60	70	3.6	3.6	3.6	3.5	3.5	3.4	0.007	0.009	0.009	0.009	0.009	0.010
	62	75	3.6	3.6	3.6	3.5	3.5	3.4	0.007	0.009	0.009	0.009	0.009	0.010
1080	60	69	3.6	3.6	3.6	3.5	3.5	3.4	0.007	0.009	0.009	0.009	0.009	0.010
	62	73	3.6	3.6	3.6	3.5	3.5	3.4	0.007	0.009	0.009	0.009	0.009	0.010

* The data in the above table are not guaranteed values.

++ Before purchase ++

【Notes before you use】

- Please verify the suitability and fitness for intended application by quality testing, evaluation or other means at your own option before any adoption, use or change of use conditions of a product listed in the datasheet.
- We would like to have a delivery specifications mutually agreed for the product that you have decided to use. The agreements defined in the delivery specifications are assigned higher priority.
- Please note that images shown may somewhat differ from the actual product in color.
- Please note that specifications and external design are subject to change for product improvement without notice.
- For details on products in the datasheet, please contact your distributor or our sales department.

【Safety Information】

- Before using the product, please read the delivery specifications carefully or contact the distributor from which you purchased the product or our sales department in order to use the product correctly.
- The products in the datasheet are Electronic circuit board materials for electronic and electrical devices. Please do not use them for other than specified use.

Please Contact us of more

【Technical Marketing】

- Japan (Osaka) TEL: 81-6-6904-2771
- USA (Mountain view) TEL: 1-408-861-3946
- Austria (Enns) TEL: 43-7223-883
- China (Guangzhou) TEL: 86-20-8713-0888

【Sales Offices】

- China (Hong Kong) TEL: 852-2529-3956
- China (Suzhou) TEL: 86-512-6825-1565
- China (Guangzhou) TEL: 86-20-8713-0888
- Korea (Seoul) TEL: 82-2-361-7873
- Taiwan (Hsinchu) TEL: 886-3-598-3201
- Thailand (Ayuthaya) TEL: 66-3533-0846
- Austria (Enns) TEL: 43-7223-883
- USA (Mountain view) TEL: 1-408-861-3946
- Japan (Osaka) TEL: 81-6-6904-2771

Panasonic Industry Co., Ltd.
 Electronic Materials Business Division
 Circuit Board Materials Business Unit.
 Head Office: 1006 Kadoma, Kadoma City, Osaka 571-8506
 TEL: 81-6-6908-1101
industrial.panasonic.com/ww/electronic-materials