

Data Sheet

**Halogen Free
& Narrow Pitch IC Substrate Materials**

MEGTRON  **Laminate R-1515A**

May. 2019 No.19053001

Specification / Laminate R-1515A

Property		Units	Test Method	Condition	Typical Value	
THERMAL	Glass Transition Temp (Tg)		C	DMA	As received	205
	Thermal Decomposition Temp (Td)			TGA		390
	Time to Delam (T260)	With Cu	min	IPC TM-650 2.4.24.1		> 120
	Time to Delam (T288)					> 120
	CTE : $\alpha 1$	X - axis	ppm / C	IPC TM-650 2.4.24	< Tg	11 - 13
		Y - axis				11 - 13
		Z - axis			30	
	CTE : $\alpha 2$	Z - axis			> Tg	140
Thermal Conductivity		W / mK	Laser Flash	25 C	0.7	
ELECTRICAL	Volume Resistivity		M Ω - cm	IPC TM-650 2.5.17.1	C-96/35/90	1 x 10 ⁹
	Surface Resistivity					M Ω
	Dielectric Constant (Dk)	1GHz	-	IPC TM-650 2.5.5.9	C-24/23/50	4.8
	Dissipation Factor (Df)					0.015
PHYSICAL	Water Absorption		%	IPC TM-650 2.6.2.1	D-24/23	0.12
	Flexural Strength	X	N / mm ²	IPC TM-650 2.4.4	As Received	500
		Y				460
	Flexural Modulus	X	GPa	JIS C6481		29
		Y				27
	Peel Strength	35 μ m	kN / m	IPC TM-650 2.4.8		1.2
	Flammability		-	UL		C-48/23/50

The sample thickness is 0.8mm.

* The data in the above table are not guaranteed values.

++ Before purchase ++

【Notes before you use】

- Please verify the suitability and fitness for intended application by quality testing, evaluation or other means at your own option before any adoption, use or change of use conditions of a product listed in the datasheet.
- We would like to have a delivery specifications mutually agreed for the product that you have decided to use. The agreements defined in the delivery specifications are assigned higher priority.
- Please note that images shown may somewhat differ from the actual product in color.
- Please note that specifications and external design are subject to change for product improvement without notice.
- For details on products in the datasheet, please contact your distributor or our sales department.

【Safety Information】

- Before using the product, please read the delivery specifications carefully or contact the distributor from which you purchased the product or our sales department in order to use the product correctly.
- The products in the datasheet are Electronic circuit board materials for electronic and electrical devices. Please do not use them for other than specified use.

Please Contact us of more

【Technical Marketing】

- Japan (Osaka) TEL: 81-6-6904-2771
- USA (Mountain view) TEL: 1-408-861-3946
- Austria (Enns) TEL: 43-7223-883
- China (Guangzhou) TEL: 86-20-8713-0888

【Sales Offices】

- China (Hong Kong) TEL: 852-2529-3956
- China (Suzhou) TEL: 86-512-6825-1565
- China (Guangzhou) TEL: 86-20-8713-0888
- Korea (Seoul) TEL: 82-2-361-7873
- Taiwan (Hsinchu) TEL: 886-3-598-3201
- Thailand (Ayuthaya) TEL: 66-3533-0846
- Austria (Enns) TEL: 43-7223-883
- USA (Mountain view) TEL: 1-408-861-3946
- Japan (Osaka) TEL: 81-6-6904-2771

Panasonic Corporation
 Industrial Solutions Company
 Electronic Materials Business Division
 Circuit Board Materials Business Unit.
 Head Office: 1006 Kadoma, Kadoma City, Osaka 571-8506
 TEL: 81-6-6908-1101
industrial.panasonic.com/ww/electronic-materials